



# External timber Fire Retardant

Timber preservation & fire retardant treatments



*Arnold Laver*



## Treated Timber Specification

Sentrin FRX fire retardant treated timber has been pressure impregnated with Exterior Fire-X, a leach resistant (Type LR), exterior grade fire retardant formulation (see <http://www.kopperspc.eu/products/fire-x.html>). It has been processed under ISO9001 controlled factory conditions to provide confidence in performance and long lasting protection without further maintenance, even in fully weather exposed situations. Treated timber can meet the requirements of national Building Regulations where Euroclass B or C are required and will significantly reduce the spread of fire, heat generation and smoke generation. These fire performance properties do not compromise critical engineering properties such as strength, durability,

### How do I specify the correct treatment?

Sentrin FRX treated wood products have been tested to BS EN 13501; Fire classification of construction products and building elements. These 'reaction to fire tests' are used to generate classifications of flammability which are commonly specified in building regulations. To specify the correct level of protection the following information is required:

1. Timber species or plywood type and dimensions.
2. Euroclass required (C or B).
3. End use application.

[Contact us](#) for assistance with detailed specification writing.

Sentrin FRX treated wood products meet the requirements of LR (leach resistant), HR (humidity resistant) and DI (dry internal) specifications.

### What is the appearance of the treated timber?

Treatment with fire retardant in general, does not alter the appearance of the timber or wood based panel. Some slight darkening may occur which will be dependent on the timber species and the kiln drying process following treatment. There may also be some surface deposits which will not affect the fire performance.

The treatment process involves pressure impregnation with a liquid polymeric resin followed by at least 72 hours in a high temperature kiln. Consideration should be given as to whether the material to be treated can withstand this process and we can provide advice.

It is always recommended that representative samples are processed prior to full scale treatment, especially if a coating is to be subsequently applied.

## Flammability Classifications

Euroclass	Transposition to BS476
A1	Non-Combustible
A2	Very limited combustibility
B	Class 0
C	Class 1
D	Class 3

### What is the Service Life of the treated wood?

Sentrin FRX treated timber has maintained its fire performance in the ASTM D2898 accelerated weathering test, which simulates over 26 years of European rainfall. Based on the evidence from testing and long term market experience, Sentrin FRX will continue to protect wood against the risk of fire, without maintenance, for the normal expected service life of timber cladding, ie 30 years.

### Typical applications

For use in above ground and exterior applications such as cladding, decking, exposed structural timber and playground equipment.

Timber can be exposed to weathering without compromising the fire performance. If a coating is required for aesthetic reasons please contact us for advice. Some coating systems may not be suitable and must be tested for their adhesion properties and fire performance, prior to application.



# User Guide



## Storage of treated timber

Following treatment, kiln drying and high temperature curing will reduce the moisture content to below 28%. Treated timber is usually wrapped following drying to protect from weathering and dirt. If extended storage is required before installation, the wrapping should be removed to promote airflow through the timber.

## Re-working of treated timber

Where possible, treated wood should not be cut or otherwise reworked as this will expose untreated wood, reducing the effectiveness of the flame retardant treatment. Rip-sawing, thicknessing and planing are not permitted. Light sanding with a fine grade sandpaper is acceptable and will not affect the fire retardant properties. Timber may be cross cut without the need for re-treatment. Refer to health & safety guidance if any re-working is to be carried out.

## Handling

Treated and dried wood poses similar hazards as untreated wood. Engineering controls and protective equipment should be used to minimise airborne wood dust.

## Metal fixtures and fastenings

Certain metal products may corrode when in direct contact with wood exposed to water. Stainless steel or hot dipped galvanised metal fittings are recommended.

## Painting and staining

Sentrin FRX treated wood contains polymeric resins which are used to improve leach resistance during weathering. Many paint systems are incompatible with the treated wood and poor adhesion may occur. Please contact us for advice on suitable coating systems. Samples should always be tested to ensure that the coating provides the intended result.



## Treatment Process

Treatment is carried out in high pressure autoclaves to penetrate fire retardant into the timber to achieve the required classification. Timber is loaded into the treatment vessel and the door sealed. A vacuum is then created inside the vessel to remove air from the timber. The vessel is flooded with fire retardant solution and high pressure is applied to penetrate into the timber. After the solution is removed a final vacuum is created to remove excess liquid. The liquid is returned to storage and there is no waste generated from the process. The freshly treated timber is then held undercover until it is drip dry before being kiln dried and then heat cured. Process times vary with the treatment specification but are typically between 90 and 240 minutes. Drying and curing can take up to 2 weeks.

## Confirmation of treatment

Every consignment of treated timber is issued with a treatment certificate which confirms the fire retardant classification. This is an important document and may be required by a building regulator. Classification reports are available to be used in conjunction with the treatment certificate. If required, individual items can be stamped with the fire classification to aid identification.

## Quality Assurance

Treatment is carried out under controlled factory conditions. The process is ISO 9001 accredited and our production centres hold Factory Production Control (FPC) certification and are WPA Benchmark FR approved. A computer controlled treatment process ensures the correct retention of fire retardant to achieve the required classification. Sentrin FRX is an impregnated fire retardant and cannot be applied by hand, brush or spray. It provides a level of confidence in performance that may not be available with treatments applied on site or in uncontrolled conditions.

## How it works

When subjected to a fire, the protection technology reacts with the combustible gases and tars normally generated by untreated wood, converting them to carbon dioxide and water. The layer of char formed on the surface insulates and retards the process of combustion reducing ignition, the rate of spread of flame, smoke propagation and the amount of heat released. This should provide increased time for escaping from a building or structure.



## Construction Products Regulations and CE marking

Under the [EU Construction Products Regulation](#) (CPR), from 1 July 2013 a construction product will need to be CE marked and accompanied by a declaration of performance if it is to be placed on the market in the European Economic Area and it is covered by either a harmonised European Product Standard or a European Technical Assessment. It is the responsibility of the company or person placing the product on the market for the first time to ensure the CE mark is correct and accurate. PTG Treatments can supply the information required to complete a Declaration of Performance (DOP).

## UK Building Regulations

The fire performance for all material that are to be used in buildings, including wood and wood based panels are stated in Document B of the UK Building Regulations:

Wall and ceiling linings are Class 1 Surface Spread of Flame in accordance with BS476:Part 7 or Euroclass C in accordance with BS EN13501.

Higher risk areas, such as escape routes and staircases, and external cladding are Class 0 (BS476:Parts 6&7) or Euroclass B (BS EN13501).

These standards relate to 'reaction to fire' of a material and not 'fire resistance' as in 30 or 60 minute specifications.

## Health Safety and Environmental

Sentrin FRX fire retardant treated timber has been pressure treated with a waterbased leach resistant (Type LR) fire retardant. Many of the health & safety recommendations are the same as those for working with untreated wood.

### Health & Safety

- Wear a dust mask, eye protection and gloves when working with wood.
- Treated wood should not be used where it may come into direct or indirect contact with drinking water.
- Do not use treated wood where the preservative may become a component of food, animal feed or beehives.
- Do not use treated wood for mulch.
- Wash exposed areas of skin following handling or working with treated timber.
- Launder heavily soiled clothes separately after working with treated timber.



### Waste Disposal

Sentrin FRX treated timber is not considered as hazardous waste. Dispose of treated wood and waste according to local authority regulation. Treated wood will not readily burn but can be disposed of in commercial incinerators or landfill to local regulations.

### Industrial Emissions Directive

Wood treatment facilities are covered by EU Industrial Emissions Directive (IED) which promotes best environmental techniques to reduce and control the impact of industrial emissions. All PTG treatment centres comply with the requirements of the IED.

### Further information

For further information on any aspect of timber protection, contact PTG Treatments. Our literature is constantly updated to reflect regulatory changes. This document is uncontrolled so please make sure you have the latest version which can be downloaded from [www.ptgtreatment.co.uk](http://www.ptgtreatment.co.uk).

# Arnold Laver

**Birmingham**  
Dudley Road  
Oldbury  
West Midlands  
B69 3DA  
T 0121 552 7788  
E [birmingham@laver.co.uk](mailto:birmingham@laver.co.uk)

**Borehamwood**  
Hertsmere Industrial Park  
Chester Road  
Borehamwood  
WD6 1WS  
T 01923 336666  
E [borehamwood@laver.co.uk](mailto:borehamwood@laver.co.uk)

**Bradford**  
Canal Road  
Bradford  
BD2 1AR  
T 01274 732861  
E [bradford@laver.co.uk](mailto:bradford@laver.co.uk)

**Bristol**  
Brabazon Hangar  
West Bay  
Filton  
BS34 7QS  
T 0117 312 1160  
E [bristol@laver.co.uk](mailto:bristol@laver.co.uk)

**Cannock**  
Unit 29 Navigation Way  
Hawks Green  
Cannock  
Staffordshire  
WS11 7XU  
T: 01543 302450  
E: [cannock@laver.co.uk](mailto:cannock@laver.co.uk)

**Coventry**  
Unit C1 Grovelands Industrial Est  
Longford  
Coventry  
CV7 9ND  
T 02476 26 3900  
E [coventry@laver.co.uk](mailto:coventry@laver.co.uk)

**Croydon**  
69 Imperial Way  
Silverwing Industrial Estate  
Croydon  
CRO 4RR  
T 0208 241 5400  
E [croydon@laver.co.uk](mailto:croydon@laver.co.uk)

**Hull**  
Crowle Street  
Hull  
HU9 1RH  
T 01482 761 220  
E [hull@laver.co.uk](mailto:hull@laver.co.uk)

**Kidderminster**  
Firs Trading Estate  
Oldington Lane  
Kidderminster  
DY11 7QN  
T 01562 66557  
E [kidderminster@laver.co.uk](mailto:kidderminster@laver.co.uk)

**Leeds**  
Pontefract Road  
Stourton  
Leeds  
LS10 1SW  
T 0113 270 4086  
E [leeds@laver.co.uk](mailto:leeds@laver.co.uk)

**Manchester**  
Liverpool Road  
Cadishead  
Manchester  
M44 5BZ  
T 0161 777 9000  
E [manchester@laver.co.uk](mailto:manchester@laver.co.uk)

**Newcastle**  
Wagonway Road  
Hebburn  
Tyne & Wear  
NE31 1SP  
T 0191 428 6666  
E [newcastle@laver.co.uk](mailto:newcastle@laver.co.uk)

**Peterborough**  
Unit 12 Kingston Park  
Flaxley Rd  
Hampton  
Peterborough  
PE2 9FT  
T 01733 74 2140  
E [peterborough@laver.co.uk](mailto:peterborough@laver.co.uk)  
**Rainham**  
124 New Road  
Rainham  
Essex  
RM13 8RS  
T 01708 529 500  
E [london@laver.co.uk](mailto:london@laver.co.uk)

**Reading**  
Basingstoke Road  
Reading  
RG2 0QN  
T 0118 975 1100  
E [reading@laver.co.uk](mailto:reading@laver.co.uk)

**Sheffield Central**  
Little London Road  
Heeley  
Sheffield  
S8 0UH  
T 0114 255 7341  
E [sheffieldcentral@laver.co.uk](mailto:sheffieldcentral@laver.co.uk)

**Sheffield Mosborough**  
Oxclose Park Road North  
Sheffield  
S20 8GN  
T 0114 276 4800  
E [sheffield@laver.co.uk](mailto:sheffield@laver.co.uk)

**Thornaby**  
Robson Avenue  
Teesside Industrial Estate  
Thornaby  
Stockton-on-Tees  
TS17 9LS  
T: 01642 751139  
E: [thornaby@laver.co.uk](mailto:thornaby@laver.co.uk)

**Look out for our new depot openings in 2020**  
Visit [laver.co.uk](http://laver.co.uk) or contact us at [enquiries@laver.co.uk](mailto:enquiries@laver.co.uk)