

# WISA®-Form MDO

WISA-Form MDO is the No. 1 panel choice for formwork applications where a matt concrete finish is desired. The medium density overlay on the face is especially designed to minimize grain transfer to the concrete face. The result is a consistent, smooth matt concrete surface. The base panel is lightweight spruce plywood which makes it easy to handle on the construction site.

## **Base board**

Plywood made solely from spruce (softwood) veneers bonded together in a cross banded construction.

# **Bonding**

Weather resistant glueing according to EN 314-2/class 3.

## Surface and edges

Face: MDO coating, for matt concrete finish.

Reverse: Dark brown phenolic film with imprinted text "WISA-Form MDO" as moisture barrier.

Edge sealing: Water resistant paint, light brown.

## Thicknesses and weight

Nominal thickness (mm)	Min.	Max.	Weight kg/m²
	thickness (mm)	thickness (mm)	(MC 10 %)
18	17.1	18.1	8.3

#### Panel size

2440 x 1220 mm

Size tolerance (length/width)  $\pm 1$  mm per metre

Squareness tolerance  $\pm 1 \, \text{mm}$  per metre length of diagonal

#### Reuses

Typical number of reuses is likely to be in the range of 10–15 times. However, the number of reuses will depend on a wide range of factors including good site practice, the required concrete finish, careful handling & storage of forms and the type and quality of release agent.

# Form release agents

The selection of the most suitable release agent will ensure cleaner striking of the forms and thus more reuses, as well as better quality concrete finishes. The chemically active release agents are considered to be the most suitable for MDO coating.

**Important note:** MDO coating is not pre-oiled and must be oiled twice before first use, and thereafter once before each subsequent reuse of the form.












# **Design Data**

Mechanical properties of WISA-Form MDO, in standard thicknesses, moisture content  $10 \pm 2 \%$ .

Nominal thickness (mm)	Average thickness	Mean modulus of elasticity bending (N/mm²)		Characteristic strength bending (N/mm²)	
		EmII	EmI-	fmII	fmI-
18	17.6	8170	3830	20.4	13.0

WISA-Form MDO is constructed with the grain direction of the outermost (face) veneers running parallel to the long edges of the panel. Therefore boards should always be used with the long edges parallel to the span direction to minimise deflection of the shutter.



Moisture content 27 %, short term loading
Partial safety factor for the material is 1.3. Partial safety factor for the loads is 1.2.
Deflection limit L/300 of the span
Support width is not taken into account in calculations

# Instructions for use

See "Guide to Good Site Practice" available from UPM.



**UPM Plywood**